

Particle Size Analysis
(CT 202)

Client: Arqlite
 Project: Lab Testing Services
 Project No.: 12315
 Sample ID: S040221-110
 Material Description: Regular
 Sample Location: Arqlite - Santa Ana

Date Sampled: 04/02/21
 Sampled By: Client
 Date Tested: 04/06/21
 Tested By: C. Fuentes
 Date Reviewed: 04/06/21
 Reviewed By: R. Jimenez


Dry Weight, g 2,570

Sieve Size	Weight Retained Grams	Percent Retained %	Percent Passing %	Specification
3" (75mm)	0	0	100	-
2" (50mm)	0	0	100	-
1 1/2" (37.5mm)	0	0	100	-
1" (25mm)	0	0	100	-
3/4" (19mm)	0	0	100	-
1/2" (12.5mm)	2,214	86	14	-
3/8" (9.5mm)	2,560	100	0	-
#4 (4.75mm)	2,570	100	0	-

Dry Weight, g

#8 (2.36mm)				-
#16 (1.18mm)				-
#30 (600um)				-
#50 (300um)				-
#100 (150um)				-
#200 (75um)				-

D ₁₀	0.30
D ₃₀	0.55
D ₆₀	1.50
C _u	#DIV/0!
C _c	#DIV/0!
Fineness Modulus	#DIV/0!



Soil Classification: -

Remarks:

Specific Gravity - Coarse Aggregate (ASSHTO T85)

Client:	Arqlite	Date Sampled:	4/2/2021
Project:	Lab Testing Services	Sampled By:	Client
Project No.:	12315	Date Tested:	04/07/21
Sample ID:	S040221-110	Tested By:	C. Fuentes
Sample Location:	Arqlite Santa Ana	Date Reviewed:	04/07/21
Material Description:	Regular	Reviewed By:	R. Jimenez

Sample No.		Specification
Dry Weight in Air (A)	2263.6	
SSD Weight in Air (B)	2322.6	
Weight in Water (C)	-624.5	
Bulk Specific Gravity (A/(B-C))	0.768	
Bulk Specific Gravity - SSD (B/(B-C))	0.788	
Specific Gravity - Apparent (A/(A-C))	0.784	
Absorption ((B-A)/A*100)	2.6	

Remarks:

This report remains the property of Sequoia Consultants and shall not be reproduced without the written consent of Sequoia Consultants or its client. This report and results apply only to the items inspected and tested.

Durability Index (CT 229)

Client:	Arqlite	Date Sampled:	04/02/21
Project:	Lab Testing Services	Sampled By:	Client
Project No.:	12315	Date Tested:	5/3/2021
Sample ID:	S040221-110	Tested By:	C. Fuentes
Material Description:	Regular	Date Reviewed:	5/4/2021
Sample Location:	Arqlite - Santa Ana	Reviewed By:	R. Jimenez

	Sand Reading	Clay Reading	Durability Index	Specifications
Durability Index - Fines			N/A	
	Sediment Height		Durability Index	
Durability Index - Coarse	0.0		100	
Durability Index			100	

Remarks: - Material tested was retained on 1/2" sieve.

Soundness of Coarse Aggregates
(ASTM C88)

Client:	Arqlite	Date Sampled:	4/2/2021
Project:	Lab Testing Services	Sampled By:	Client
Project Number:	12315	Date Tested:	Various
Sample ID:	S040221-110	Tested By:	J. Uranga
Sample Location:	Arqlite - Santa Ana	Date Reviewed:	6/4/2021
Material Description:	Regular	Reviewed By:	R. Jimenez

Aggregate Test Sizes	Weighted Average Loss, %	Specifications
3/4" - 3/8", (Sodium Sulfate)	0.0	
3/4" - 3/8", (Magnesium Sulfate)	0.0	

Remarks:

Particle Size Analysis
(CT 202)

Client: Arqlite
 Project: Lab Testing Services
 Project No.: 12315
 Sample ID: S040221-111
 Material Description: Mini
 Sample Location: Arqlite - Santa Ana

Date Sampled: 04/02/21
 Sampled By: Client
 Date Tested: 04/06/21
 Tested By: C. Fuentes
 Date Reviewed: 04/06/21
 Reviewed By: R. Jimenez


Dry Weight, g 1,107

Sieve Size	Weight Retained Grams	Percent Retained %	Percent Passing %	Specification
3" (75mm)	0	0	100	-
2" (50mm)	0	0	100	-
1 1/2" (37.5mm)	0	0	100	-
1" (25mm)	0	0	100	-
3/4" (19mm)	0	0	100	-
1/2" (12.5mm)	0	0	100	-
3/8" (9.5mm)	336	30	70	-
#4 (4.75mm)	1,104	100	0	-

Dry Weight, g 0.0

#8 (2.36mm)	1,107.0	100	0	-
#16 (1.18mm)				-
#30 (600um)				-
#50 (300um)				-
#100 (150um)				-
#200 (75um)				-

D ₁₀	0.30
D ₃₀	0.55
D ₆₀	1.50
C _u	5.00
C _c	0.67
Fineness Modulus	6.30



Soil Classification: -

Remarks:

Specific Gravity - Coarse Aggregate (ASSHTO T85)

Client:	Arqlite	Date Sampled:	4/2/2021
Project:	Lab Testing Services	Sampled By:	Client
Project No.:	12315	Date Tested:	04/07/21
Sample ID:	S040221-111	Tested By:	C. Fuentes
Sample Location:	Arqlite Santa Ana	Date Reviewed:	04/07/21
Material Description:	Mini	Reviewed By:	R. Jimenez

Sample No.		Specification
Dry Weight in Air (A)	1071.2	
SSD Weight in Air (B)	1130.0	
Weight in Water (C)	-530.4	
Bulk Specific Gravity (A/(B-C))	0.645	
Bulk Specific Gravity - SSD (B/(B-C))	0.681	
Specific Gravity - Apparent (A/(A-C))	0.669	
Absorption ((B-A)/A*100)	5.5	

Remarks:

This report remains the property of Sequoia Consultants and shall not be reproduced without the written consent of Sequoia Consultants or its client. This report and results apply only to the items inspected and tested.

Durability Index
(CT 229)

Client:	Arqlite	Date Sampled:	04/02/21
Project:	Lab Testing Services	Sampled By:	Client
Project No.:	12315	Date Tested:	5/3/2021
Sample ID:	S040221-111	Tested By:	C. Fuentes
Material Description:	Mini	Date Reviewed:	5/4/2021
Sample Location:	Arqlite - Santa Ana	Reviewed By:	R. Jimenez

	Sand Reading	Clay Reading	Durability Index	Specifications
Durability Index - Fines			N/A	
	Sediment Height		Durability Index	
Durability Index - Coarse	0.0		100	
Durability Index			100	

Remarks: - Material tested was retained on 3/8" and #4 sieve.

Soundness of Coarse Aggregates
(ASTM C88)

Client:	Arqlite	Date Sampled:	4/2/2021
Project:	Lab Testing Services	Sampled By:	Client
Project Number:	12315	Date Tested:	Various
Sample ID:	S040221-111	Tested By:	J. Uranga
Sample Location:	Arqlite - Santa Ana	Date Reviewed:	6/4/2021
Material Description:	Mini	Reviewed By:	R. Jimenez

Aggregate Test Sizes	Weighted Average Loss, %	Specifications
3/4" - 3/8", 3/8" - #4 (Sodium Sulfate)	0.0	
3/4" - 3/8", 3/8" - #4 (Magnesium Sulfate)	1.0	

Remarks:

Particle Size Analysis (CT 202)

Client: Arqlite
 Project: Lab Testing Services
 Project No.: 12315
 Sample ID: S040221-112
 Material Description: Micro-Mini
 Sample Location: Arqlite - Santa Ana

Date Sampled: 04/02/21
 Sampled By: Client
 Date Tested: 04/06/21
 Tested By: C. Fuentes
 Date Reviewed: 04/06/21
 Reviewed By: R. Jimenez


Dry Weight, g 1,103

Sieve Size	Weight Retained Grams	Percent Retained %	Percent Passing %	Specification
3" (75mm)	0	0	100	-
2" (50mm)	0	0	100	-
1 1/2" (37.5mm)	0	0	100	-
1" (25mm)	0	0	100	-
3/4" (19mm)	0	0	100	-
1/2" (12.5mm)	0	0	100	-
3/8" (9.5mm)	0	0	100	-
#4 (4.75mm)	18	2	98	-

Dry Weight, g 0.0

#8 (2.36mm)	1,099.8	100	0	-
#16 (1.18mm)	1,103.0	100	0	-
#30 (600um)				-
#50 (300um)				-
#100 (150um)				-
#200 (75um)				-

D ₁₀	0.30
D ₃₀	0.55
D ₆₀	1.50
C _u	5.00
C _c	0.67
Fineness Modulus	5.01



Soil Classification: -

Remarks:

Specific Gravity - Coarse Aggregate (ASSHTO T85)

Client:	Arqlite	Date Sampled:	4/2/2021
Project:	Lab Testing Services	Sampled By:	Client
Project No.:	12315	Date Tested:	04/07/21
Sample ID:	S040221-112	Tested By:	C. Fuentes
Sample Location:	Arqlite Santa Ana	Date Reviewed:	04/07/21
Material Description:	Micro-Mini	Reviewed By:	R. Jimenez

Sample No.		Specification
Dry Weight in Air (A)	921.6	
SSD Weight in Air (B)	1104.4	
Weight in Water (C)	-205.7	
Bulk Specific Gravity (A/(B-C))	0.703	
Bulk Specific Gravity - SSD (B/(B-C))	0.843	
Specific Gravity - Apparent (A/(A-C))	0.818	
Absorption ((B-A)/A*100)	19.8	

Remarks:

This report remains the property of Sequoia Consultants and shall not be reproduced without the written consent of Sequoia Consultants or its client. This report and results apply only to the items inspected and tested.

Durability Index (CT 229)

Client:	Arqlite	Date Sampled:	04/02/21
Project:	Lab Testing Services	Sampled By:	Client
Project No.:	12315	Date Tested:	5/3/2021
Sample ID:	S040221-112	Tested By:	C. Fuentes
Material Description:	Micro-Mini	Date Reviewed:	5/4/2021
Sample Location:	Arqlite - Santa Ana	Reviewed By:	R. Jimenez

	Sand Reading	Clay Reading	Durability Index	Specifications
Durability Index - Fines			N/A	
	Sediment Height		Durability Index	
Durability Index - Coarse	0.0		100	
Durability Index			100	

Remarks: - Material tested was retained on #4 sieve.

Soundness of Coarse Aggregates
(ASTM C88)

Client:	Arqlite	Date Sampled:	4/2/2021
Project:	Lab Testing Services	Sampled By:	Client
Project Number:	12315	Date Tested:	Various
Sample ID:	S040221-112	Tested By:	J. Uranga
Sample Location:	Arqlite - Santa Ana	Date Reviewed:	06/04/2021
Material Description:	Micro-Mini	Reviewed By:	R. Jimenez

Aggregate Test Sizes	Weighted Average Loss, %	Specifications
#4 - #8 (Sodium Sulfate)	0.0	
#4 - #8 (Magnesium Sulfate)	0.0	

Remarks: